Coefficient d'absorption acoustique pondéré $\alpha_w$ selon EN ISO 11654

# SonicVoid 2600

Rideau acoustique occultant, **double couche** · code produit 45002

COEFFICIENT D'ABSORPTION ACOUSTIQUE PONDÉRÉ

$\alpha_w = 1{,}00$

Classe d'absorption

**A**

selon EN ISO 11654

## 1. Coefficients d'absorption mesurés par bandes de tiers d'octave

| F [HZ] | 100 | 125 | 160 | 200 | 250 | 315 | 400 | 500 | 630 | 800 | 1 000 | 1 250 | 1 600 | 2 000 | 2 500 | 3 150 | 4 000 | 5 000 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| $\alpha_s$ | 0,13 | 0,27 | 0,45 | 0,58 | 0,75 | 0,92 | 1,00 | 1,08 | 1,10 | 1,13 | 1,14 | 1,11 | 1,10 | 1,12 | 1,09 | 1,13 | 1,15 | 1,19 |

Source des valeurs : rapport RAL™-A19-502, page 5 (annexe du présent document).

## 2. Absorption par fréquence




coefficient d'absorption mesuré $\alpha_s$ (plus c'est foncé, plus il absorbe)

courbe de référence ISO 11654 pour $\alpha_w = 1{,}00$

## 3. Classe d'absorption acoustique

| E | D | C | B | A |
|---|---|---|---|---|
| 0,15–0,25 | 0,30–0,55 | 0,60–0,75 | 0,80–0,85 | 0,90–1,00 |

▲ SonicVoid 2600: $\alpha_w = 1{,}00$ → classe A

## 4. Calcul selon EN ISO 11654

| OCTAVE [HZ] | $A_S$ TIERS D'OCTAVE | MOYENNE | $A_P$ | COURBE RÉF. | ÉCART DÉFAVORABLE |
|---|---|---|---|---|---|
| 125 | 0,13 · 0,27 · 0,45 | 0,283 | **0,30** | – | – |
| 250 | 0,58 · 0,75 · 0,92 | 0,750 | **0,75** | 0,80 | 0,05 |
| 500 | 1,00 · 1,08 · 1,10 | 1,060 | **1,00*** | 1,00 | 0,00 |
| 1 000 | 1,13 · 1,14 · 1,11 | 1,127 | **1,00*** | 1,00 | 0,00 |
| 2 000 | 1,10 · 1,12 · 1,09 | 1,103 | **1,00*** | 1,00 | 0,00 |
| 4 000 | 1,13 · 1,15 · 1,19 | 1,157 | **1,00*** | 0,90 | 0,00 |
| **Somme des écarts défavorables (250–4 000 Hz)** — limite de la norme ≤ 0,10 | | | | | **0,05** |

* Moyenne arrondie à 0,05 et plafonnée à 1,00 selon la norme. La courbe de référence (0,80 / 1,00 / 1,00 / 1,00 / 0,90) est décalée par pas de 0,05 vers le bas jusqu'à ce que la somme des écarts défavorables ne dépasse pas 0,10. À la valeur 1,00 dans la bande de 500 Hz, la somme est de 0,05, donc $\alpha_w$ = 1,00. Aucun indicateur de forme (L, M, H) – aucun $\alpha_p$ ne dépasse la courbe de 0,25 ou plus. Selon l'annexe B de la norme, $\alpha_w$ 0,90–1,00 correspond à la classe d'absorption A.

## 5. Mesure de laboratoire de référence

| | |
|---|---|
| Laboratoire | Riverbank Acoustical Laboratories, 1512 S Batavia Ave, Geneva, IL, USA — accréditation NVLAP (Lab Code 100227-0), ISO/IEC 17025:2017 |
| Rapport | RAL™-A19-502, mesure du 06/12/2019, émis le 08/01/2020 |
| Méthode | ASTM C423-17, chambre réverbérante 291,98 m³, 21,4 °C, 55 % HR |
| Montage | type G-115 selon ASTM E795-16 (modifié) : deux couches suspendues avec un espace de 76 mm, à 76 mm du mur de la chambre, bords non scellés |
| Échantillon | Acoustic Blanket, Producer's Choice (VB-77G), fabricant Vocal Booth To Go, 2 × 2 032 × 2 692 mm |
| Écart par rapport à la norme | surface de l'échantillon 5,47 m² (ASTM C423 exige min. 5,57 m²) — indiqué dans le rapport |

## 6. Avertissement

Ce document a été émis par VocalBoothToGo-EU s.r.o. Il ne s'agit pas d'un rapport de laboratoire et Riverbank Acoustical Laboratories n'en est pas l'auteur. La valeur $\alpha_w$ est calculée selon EN ISO 11654 à partir des coefficients d'absorption par tiers d'octave mesurés par le laboratoire selon la méthode ASTM C423, analogue à EN ISO 354 (chambre réverbérante).

Les résultats s'appliquent à l'échantillon testé et au montage indiqué. Le rapport original du laboratoire est joint sans modification en annexe.

**Annexe :** rapport de Riverbank Acoustical Laboratories RAL™-A19-502 (9 pages, original).

Établi par : VocalBoothToGo-EU s.r.o.

Date : 28/09/2026

# Test Report

SPONSOR: **Vocal Booth To Go**
Frederick, MD

**Sound Absorption**
**RAL™-A19-502**

CONDUCTED: 2019-12-06



ON: Acoustic Blanket, Producer's Choice - dual layer (Modified Type G-115 Mounting, specimen undersized)

## TEST METHODOLOGY

Riverbank Acoustical Laboratories™ is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2017 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-17: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method," with the single exception that the specimen area of 5.47 $m^2$ was less than the minimum area of 5.57 $m^2$ specified in Section 9.1.1 of the standard. Refer to the mounting description on Page 2 for details. The specimen mounting was performed according to the Type G Mounting described in Section 12 of ASTM E795-16: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests," with the single exception that the top edge of the specimen was not closed off. A description of the measurement procedure and room specifications are available upon request. The results presented in this report apply to the sample as received from the test sponsor.

## INFORMATION PROVIDED BY SPONSOR

The test specimen was designated by the sponsor as Acoustic Blanket, Producer's Choice - dual layer (Modified Type G-115 Mounting, specimen undersized). The following nominal product information was provided by the sponsor prior to testing. The accuracy of such sponsor-provided information can affect the validity of the test results.

**Product Under Test**

| | |
|---|---|
| Trade Name: | Acoustic Blanket, Producer's Choice |
| Material ID: | VB-77G |
| Manufacturer: | Vocal Booth To Go |

## SPECIMEN MEASUREMENTS & TEST CONDITIONS

Through a full external visual inspection performed on the test specimen, Riverbank personnel verified the following information:

**Test Specimen**

| | |
|---|---|
| Material: | Quilted blanket |
| Dimensions: | 2 @ 2032 mm (80 in.) x 2692.4 mm (106 in.) |
| Thickness: | 7.26 mm (0.286 in.) each |
| Overall Weight: | 12.02 kg (26.5 lbs) |

*Note: The specimen was cut to the given dimensions from larger samples. The cut edges of the specimen material were sealed with duct tape.*

NVLAP TESTING
NVLAP LAB CODE 100227-0

RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

**Overall Specimen Properties**

| | |
|---|---|
| Size: | 2.03 m (80.0 in) wide by 2.69 m (106.0 in) long |
| Thickness: | 0.09 m (3.572 in) |
| Weight: | 12.02 kg (26.5 lbs) |
| Mass per Unit Area: | 2.2 kg/m² (0.45 lbs/ft²) |
| Calculation Area: | 5.471 m² (58.89 ft²) |

**Test Environment**

| | |
|---|---|
| Room Volume: | 291.98 m³ |
| Temperature: | 21.4 °C ± 0.1 °C (Requirement: ≥ 10 °C and ≤ 5 °C change) |
| Relative Humidity: | 54.95 % ± 1.1 % (Requirement: ≥ 40 % and ≤ 5 % change) |
| Barometric Pressure: | 99.6 kPa (Requirement not defined) |

MOUNTING METHOD

Modified Type G-115 Mounting: The test specimen was hung using a stand provided by the test sponsor. The specimen was cut to the dimensions given above to accommodate the limited height of the stand. An array of 76.2 mm (3 in.) wide wooden spacers was used to space the specimen layers approximately 76.2 mm (3 in.) apart. The hung specimen was placed in the test chamber with a 76 mm (3.0 in.) wide gap between the vertical test surface and the nearest layer of sample material. The distance between the vertical test surface and the centerline of the specimen was approximately 114 mm (4.5 in.). The numeral suffix in the mounting designation is the distance in millimeters between the vertical test surface and the centerline of the test specimen, rounded to the nearest integer multiple of 5. Perimeter edges were left unsealed. All modifications to the standard mounting practice were intended to better represent the typical field condition, as described by the test sponsor.

Figure 1 – Specimen mounted in test chamber

Figure 2 – Detail of single layer of specimen material

NVLAP TESTING
NVLAP LAB CODE 100227-0

RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.
THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

Figure 3 – Detail of hanging method, spacer

NVLAP TESTING
NVLAP LAB CODE 100227-0

RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.
THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

TEST RESULTS

Specimen total absorption and absorption coefficient are tabulated at the eighteen standard frequencies. A graphic presentation of the data and additional information appear on the following pages.

| 1/3 Octave Center Frequency (Hz) | Total Absorption ($m^2$) | Total Absorption (Sabins) | Absorption Coefficient |
|---|---|---|---|
| 100 | 0.70 | 7.57 | 0.13 |
| ** 125 | 1.50 | 16.13 | 0.27 |
| 160 | 2.49 | 26.75 | 0.45 |
| 200 | 3.16 | 34.00 | 0.58 |
| ** 250 | 4.12 | 44.34 | 0.75 |
| 315 | 5.05 | 54.38 | 0.92 |
| 400 | 5.47 | 58.84 | 1.00 |
| ** 500 | 5.91 | 63.57 | 1.08 |
| 630 | 6.04 | 65.02 | 1.10 |
| 800 | 6.18 | 66.48 | 1.13 |
| ** 1000 | 6.26 | 67.41 | 1.14 |
| 1250 | 6.08 | 65.40 | 1.11 |
| 1600 | 6.03 | 64.89 | 1.10 |
| ** 2000 | 6.13 | 65.96 | 1.12 |
| 2500 | 5.97 | 64.24 | 1.09 |
| 3150 | 6.18 | 66.47 | 1.13 |
| ** 4000 | 6.31 | 67.93 | 1.15 |
| 5000 | 6.51 | 70.11 | 1.19 |

**SAA = 1.01**
**NRC = 1.00**

TEST RESULTS (continued)

The sound absorption average (SAA) is defined in ASTM C423-17 Section 3.1.1 as the arithmetic average of the sound absorption coefficients of a material for the twelve one-third octave bands from 200 Hz through 2500 Hz, inclusive, rounded to the nearest integer multiple of 0.01.

The noise reduction coefficient (NRC) is defined from previous versions of ASTM C423 as the arithmetic average of the sound absorption coefficients at 250 Hz, 500 Hz, 1000 Hz, and 2000 Hz, rounded to the nearest integer multiple of 0.05.

Tested by _____
Marc Sciaky
*Senior Experimentalist*

Report by _____
Malcolm Kelly
*Acoustical Test Engineer*

Approved by _____
Eric P. Wolfram
*Laboratory Manager*

Digitally signed by
Eric P Wolfram
Location: Geneva, IL
Date: 2020.01.08
10:08:07 -06'00'

NVLAP TESTING
NVLAP LAB CODE 100227-0

RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.
THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

# SOUND ABSORPTION REPORT

Acoustic Blanket, Producer's Choice - dual layer
(Modified Type G-115 Mounting, specimen undersized)




**SAA = 1.01**
**NRC = 1.00**

NVLAP TESTING
NVLAP LAB CODE 100227-0

RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.
THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

## APPENDIX A: Extended Frequency Range Data

Specimen: Acoustic Blanket, Producer's Choice - dual layer (Modified Type G-115 Mounting, specimen undersized) (See Full Report)

*The following non-accredited data were obtained in accordance with ASTM C423-17, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.*

| 1/3 Octave Band Center Frequency (Hz) | **Total Absorption** (Sabins) | **Absorption Coefficient** |
|---|---|---|
| 31.5 | 2.13 | 0.04 |
| 40 | 3.38 | 0.06 |
| 50 | -4.16 | -0.07 |
| 63 | -8.70 | -0.15 |
| 80 | 2.21 | 0.04 |
| 100 | 7.57 | 0.13 |
| 125 | 16.13 | 0.27 |
| 160 | 26.75 | 0.45 |
| 200 | 34.00 | 0.58 |
| 250 | 44.34 | 0.75 |
| 315 | 54.38 | 0.92 |
| 400 | 58.84 | 1.00 |
| 500 | 63.57 | 1.08 |
| 630 | 65.02 | 1.10 |
| 800 | 66.48 | 1.13 |
| 1000 | 67.41 | 1.14 |
| 1250 | 65.40 | 1.11 |
| 1600 | 64.89 | 1.10 |
| 2000 | 65.96 | 1.12 |
| 2500 | 64.24 | 1.09 |
| 3150 | 66.47 | 1.13 |
| 4000 | 67.93 | 1.15 |
| 5000 | 70.11 | 1.19 |
| 6300 | 68.63 | 1.17 |
| 8000 | 72.24 | 1.23 |
| 10000 | 75.45 | 1.28 |
| 12500 | 74.59 | 1.27 |

## APPENDIX B: Instruments of Traceability

Specimen: Acoustic Blanket, Producer's Choice - dual layer (Modified Type G-115 Mounting, specimen undersized) (See Full Report)

| Description | Model | Serial Number | Date of Certification | Calibration Due |
|---|---|---|---|---|
| System 1 | Type 3160-A-042 | 3160-106968 | 2019-06-25 | 2020-06-25 |
| Bruel & Kjaer Mic And Preamp A | Type 4943-B-001 | 2311428 | 2019-09-27 | 2020-09-27 |
| Bruel & Kjaer Pistonphone | Type 4228 | 2781248 | 2019-08-09 | 2020-08-09 |
| Omega Digital Temp., Humid. And Pressure Recorder | OM-CP-PRHTemp2000 | P97844 | 2019-02-08 | 2020-02-08 |

## APPENDIX C: Revisions to Original Test Report

Specimen: Acoustic Blanket, Producer's Choice - dual layer (Modified Type G-115 Mounting, specimen undersized) (See Full Report)

| Date | Revision |
|---|---|
| 2020-01-08 | Original report issued |

END



RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.
THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.